



Elastron

D100.A72.N

TECHNICAL DATASHEET

PRODUCT DESCRIPTION

A soft , colorable SBS based thermoplastic elastomer (TPE) compound designed for injection molding applications.

GENERAL PROPERTIES

Color Natural
Certifications RoHS
Processing Method Injection
Available Standards ASTM

Physical Properties					
Property	Unit	Standard	Value		
Density	g/cm³	ASTM D 792	1.09		
Durometer Hardness, 3 sec	Shore A	ASTM D 2240	72.00		
Tensile Strength at Break	MPa	ASTM D412, Method A	3.50		
Mod.of Elasticity %100	MPa	ASTM D412, Method A	2.40		
Mod.of Elasticity %300	MPa	ASTM D412, Method A	3.10		
Elongation at break	%	ASTM D412, Method A	450.00		
Compression Set	% at 23°C, 22 h	ASTM D 395, Type 2, Method B	25.00		
Tear Resistance	N/mm	ASTM D624	23.00		

FR07.03.16 Rev.06 Rev.00002 Page 1/3





Elastron

D100.A72.N

Ageing Tests				
Ozone Resistance	Stressed	ASTM D 1149		
Bondable to				

PE-PP-EVA

Processing					
Injection	Unit	Value			
Drying temperatures	°C	-			
Drying time	hours	No need			
Rear Zone temp.	°C	140-150			
Middle Zone temp.	°C	145-160			
Front Zone temp.	°C	150-165			
Nozzle Temperature	°C	165-185			
Injection Speed	-	Low			
Injection Time	sec.	3-5			
Injection Pressure	bar	10-40			
Hold Pressure	bar	5-20			
Back Pressure	bar	5-40			
Screw Speed	rpm	50-200			
Mold Temperature	°C	25-50			
Screw Comp. ratio	-	1.5:1- 2.0:1			
Screw L/D ratio	-	18-24			
Residence time	-	1-2 shot			
Cushion size	mm	8			
Suggested Max Regrind	%	-			

FR07.03.16 Rev.06 Rev.00002 Page 2 / 3





Elastron

D100.A72.N

Additional Information

Elastron products are not compatible with PVC and Acetal.

Regrinding level up to %20 is recommended with minimum property loss.

Shrinkage	Unit	Standard	Value
Flow	%	ASTM D955	3.00
Across Flow	%	ASTM D955	1.54

Notes

The company name, the brand, the logo and all kinds of visuals and writings in this document are the property of Elastron. It cannot be copied, distributed, modified or reproduced without the express written permission of Elastron. Independently, these documents can only be printed for personal use. However, in any case, the visuals and writings contained here cannot be used in another document or web page.

All the visuals, texts, information and explanations and the like in this document are for promotional purposes, giving information and providing convenience to the user. The values presented in this document apply only to the product mentioned above and cannot be extended to other products in general. Elastron is not responsible for the results that may arise from tests outside the control of Elastron. Although Elastron bases the information and suggestions contained herein on reliable data, it does not guarantee that such information and suggestions are correct and that the product is suitable for its intended use.

The user should know that Elastron must obtain the final information before taking any action by referring to the information and suggestions contained in this document.

Elastron reserves the right, at its discretion, to change or terminate the content of the document at any time and in any way.

ISO 9001: 2015 & IATF16949: 2016 & ISO 14001: 2015 REGISTERED QUALITY SYSTEMS









FR07.03.16 Rev.06 Rev.0002 Page 3 / 3